

Technical data sheet Version 2

Bonding primer BETONCONTACT

ТУ 2316-003-49630959-04

Destination For preparing various types of surfaces (concrete, brick, wood, cement, gypsum, gypsum plasterboard, ceramic) for all types of decorative finishing (puttying, painting, etc.).

Properties Reduces porosity of treated surfaces, increases adhesion. Does not have an unpleasant odor. Can be used on walls previously painted with oil or pentaphthalic paint.

Composition Acrylic copolymer
Quartz filler
Processing aids
Pigment
Water

Packaging Plastic containers of 1.5 kg, 3.5 kg, 7 kg, 14 kg

Technical Specifications

Appearance	Pink colored compound
Film appearance after drying	Smooth, no visible inclusions
Bruckfield viscosity, cPs, sp. 7, V=20 rpm	10000-30000
Mass fraction of non-volatile substances, %, min	50
Film resistance to static action of water at (20±2)°C, h, no less	24
Frost resistance, cycles	5
pH	7-8
Drying time up to degree 3	1
at (20±2) oC, hour, not more	24

Storage conditions Store in a tightly closed container, away from heaters and direct sunlight, at a temperature not lower than +5oC. In case of freezing products thaw at room temperature and mix thoroughly until homogeneous mass. After thawing it completely retains its properties.

Guaranteed shelf life

In unopened container manufacturer 24 months from the date of manufacture.

Transportation

By all means of transport in conditions excluding the influence of atmospheric factors (covered vans, wagons, etc.). Duration of transportation at temperatures below 0°C should not exceed 1 month. Product does not belong to dangerous goods. Code of emergency measures is not required.

Waste management

Containers and unused remains of primer after drying are disposed as household waste.

Security

Products are fire and explosion-proof and non-toxic. Use personal hand protection equipment. When using the product do not smoke, do not drink, do not eat. In case of contact with skin and eyes wash with water. Keep out of reach of children. Avoid contact with water and soil.

All information is correct on the day of publication. Published technical data and instructions are subject to change without notice.